



OVENRITE 200

	Typical Value	Unit
Material combination	PA, PET	
Reel length	350	m
Total thickness	200	µm
Grammage	272	g/m ²
Yield	3.7	m ² /kg

Technical data

	Typical Value	Unit	Test Method
Water vapour transmission ¹	8	g/m ² /24 h	ASTM E 96
O ₂ –transmission ²	10	cm ³ /m ² /24 h	ASTM D 3985
N ₂ –transmission ²	1.8	cm ³ /m ² /24 h	(theoretical)
CO ₂ –transmission ²	45	cm ³ /m ² /24 h	(theoretical)
Puncture resistance	22	N	DIN EN 14477
Haze	4	%	ASTM D 1003
Gloss (60°)	140	%	ASTM D 2457
Forming temperature range	100-120	°C	

Food compliance



Regulation (EC) No 1935/2004
 Regulation (EC) No 2023/2006
 Regulation (EU) No 10/2011, as amended
 Directive 94/62/EC, as amended

Your contact

BEMIS Valkeakoski Oy
 P.O. Box 70
 37601 VALKEAKOSKI
 FINLAND
 Tel: +358 (0)207 51 3100
 Fax: +358 (0)207 51 3138
www.bemis-europe.com

Recommended storage conditions: 5-25 °C, 30-60 % RH, for up to 12 months, except for AF products 6 months. Store in a clean dry place away from direct heat and direct sunlight. Keep in original packaging until ready for use.

IMPORTANT: The typical values documented were determined by statistical analyses of limited sample size, and they are subject to revision as additional information is gained. The typical data is meant for comparative purposes only. Customers are solely responsible for determining the suitability of this product for their intended use.

¹ At conditions: 38 °C, 90 % RH, 1 atm

² At conditions: 23 °C, 50 % RH, 1 atm